Oxygen & Argon Works Ltd.	Spec.No.G-08.001	
Product Sales Control	Issue: C	Date:14.02.2008
GAS SPECIFICATION	Sheet 1 of 1	

## **CARBON DIOXIDE - Technical**

## **Typical Impurity Limits:**

Carbon dioxide:  $\geq 99.5\%$ Carbon monoxide:  $\leq 10 \text{ ppm}$ Moisture:  $\leq 250 \text{ ppm}$ Oil:  $\leq 20 \text{ mg/m}^3$ Others  $(O_2, N_2, H_2)$ :  $\leq 0.4\%$ 

Above specification applies to Carbon Dioxide for welding, Fire fighting etc. Israel standard 388 recommends a purity of 99.7% for welding.

Quality Assurance - According to Suppliers' QC procedures.

Manufacture - By a fermentation process or from the burning of a fuel.

<u>Packing & Distribution</u> - As a liquid in high pressure gas cylinders.

<u>Valve Outlet Thread</u> - According to IS 637 part 3. [21.7mm Whitworth, 14 teeth/", Male, Cylindrical, right hand, with rupture disk]

Approved Supplier - GORDON GASES or OXYGEN STORES.

Hazardous Materials Codes				
	U.N. No.	Emergency Actions	Hazard Class	
GAS	1013	2T	2.2	
		•	11	ראינבור מיציה
	727			

